

CONCRECRESIVE[®] 1441 MET W&S

Epoxy adhesive for segmental construction

Description

CONCRECRESIVE 1441 is an epoxy resin based bonding system available in two grades for use in two different ranges of concrete surface temperature.

CONCRECRESIVE 1441 W for 10-35°C.

CONCRECRESIVE 1441 S for 30-55°C.

Both the grades are two part systems. The two parts are distinctly coloured to facilitate proper mixing - a white coloured Base and a black coloured Reactor, which on correct mixing in the ratio 2:1 by weight, yields a uniformly grey coloured bonding paste.

Recommended for

CONCRECRESIVE 1441 is recommended for bonding two rigid elements exposed to sustained loads especially at the bond line, such as:

- bonding precast bridge elements.
- bonding external steel reinforcing plates for strengthening beams, columns, slabs.
- anchoring bolts, dowels, steel bars in concrete, etc.
- bonding the ends of concrete or metal pipes used to transport water or sewage.

Features and benefits

High HDT (heat deflection temp) Resistance to creep even at high service temperatures.

Thixotropic No loss of bond due to sagging of bond film.

High bond Durable bond.

strengths

Good bond to damp surfaces Advantage in humid environments.

Long open time Sufficient time for alignment and bonding of elements.

Packaging

Both S and W grades of CONCRECRESIVE 1441 are available in 12.5kg packs.

*Typical performance data

(in N/mm² after 7 days cure)

	1441 W	1441 S
Compressive strength	75	75
Slant shear strength (Nmm ²)	>12	>12

Properties

	1441 W	1441 S
Supply form Parts A & B	Viscous paste	Viscous paste
Colour Base	White	White
Reactor	Black	Black
Mixed	Grey	Grey
Density (mixed)	1.66kg/L	1.72 kg/L
Min. application temperature	10°C	35°C
Surface temperature for application	10-35°C	30-55°C
Non sag thickness	3 mm	3 mm
Min. pot life. (2 L)	20 Mins @ 32°C	20 Mins @ 55°C
Min. open time.	60 Mins @ 32°C	60 Mins @ 55°C
Cure time	7 days	7 days



The Chemical Company

CONCRESLIVE[®] 1441 MET W&S

Application

Surface preparation

Correct substrate preparation is critical for optimum performance. Surfaces should be structurally sound, clean, and free from loose particles, oil, grease, or any other contaminants.

Remove oil grease and wax contaminants by scrubbing with industrial grade detergent or degreasing compounds followed by mechanical cleaning.

Remove cement laitence, loose particles, mould release agent, curing membrane, and other contaminants from the surface by wet grit blasting, high pressure water jetting (approximately 150 bars) or such other effective methods.

For smoothing deep surface irregularities, use CONCRESLIVE 1441 mixed with graded sand in the ratio 1:1 by weight.

Mixing

Mechanical mixing is necessary. A slow speed (600 rpm) drill with a grout stirrer is recommended.

Mix the entire contents of both Base and Reactor containers together to avoid batching errors.

However, if part mixing is necessary, stir each component individually and then measure out precisely each component in the correct ratio into a clean, dry pail for subsequent mixing. Ensure that the remaining contents of each container are not contaminated.

Mix Base and Reactor together until the streaks of black and white disappear to yield a homogenous grey mix.

Prepare both the surfaces that are to be bonded in the accordance with the above.

Placing

If the surface has been treated with a fairing coat as described above, allow the fairing coat to set and within 24 hours apply CONCRESLIVE 1441 on one of the two surfaces being bonded.

Apply CONCRESLIVE 1441 within its pot life to a thickness of 2 mm to 3 mm using a trowel, so as to allow for a small quantity of the bonding material to extrude out of the bond line when pressure is applied to bond the two surfaces.

The prepared surfaces of the two rigid elements to be bonded should be brought together within the open time of the product and retained in position until CONCRESLIVE 1441 cures.

Cleaning

Clean the tools and equipment with SOLVENT NO. 2 before the bonding agent hardens.

Estimating data

Material requirement is 1 L / m² at 1 mm thickness.

Shelf life

CONCRESLIVE 1441 can be stored in tightly sealed original packing for 12 months, if stored at a temperature below 30°C.

Precaution

Health: CONCRESLIVE 1441 contains certain chemicals which can cause skin irritation if exposed and respiratory reaction if inhaled. Wear gloves, masks and use barrier creams such as Kerodex No 71 while handling the product. Wash thoroughly after handling.



The Chemical Company

CONGRESIVE[®] 1441 MET W&S

Should skin contact occur, wash immediately with soap and water, or an effective hand cleaner.

In case of accidental eye contact wash with copious quantities of water and seek medical help immediately.

If ingested, do not induce vomiting. Consult doctor immediately.

The vapours of solvents used for cleaning can be irritating. It is therefore recommended that cleaning is done in well ventilated areas.

Fire: CONGRESIVE 1441 is combustible. Avoid exposure to naked flame. Do not smoke while handling the product.

05/2006 BASF_CC-UAE revised 03/2007

* Properties listed are based on laboratory controlled tests.

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

As all BASF technical datasheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue.

BASF Construction Chemicals UAE LLC

P.O. Box 37127, Dubai, UAE

Tel: +971 4 8090800

www.basf-cc.ae

Fax: +971 4 8851002

e-mail: marketingcc.mideast@basf.com



Certificate No.
963680



Certificate No.
945787



Certificate No.
772556