



The Chemical Company

MASTERTOP[®] PRIMER 2

Two-component solvent free epoxy surface sealer and primer

Description

MASTERTOP[®] PRIMER 2 is a high grade; low-viscosity, two-component epoxy primer and surface sealer. MASTERTOP[®] PRIMER 2 is used as a sealer or scratch coat with, and without, the addition of quartz sand.

Primary uses

MASTERTOP[®] PRIMER 2 is suitable for the sealing of concrete surfaces, as well as for the filling of fissures and joints. To improve adhesion MASTERTOP[®] PRIMER 2 is sprinkled with quartz sand while still wet to create a mechanical key for subsequent coatings.

MASTERTOP[®] PRIMER 2 may be mixed with sand to the desired consistency to repair patches or form coverings. In either case the mixed mortar must be applied to a surface previously coated with MASTERTOP[®] PRIMER 2 resin and whilst still tacky. Consult your BASF representative.

Colours

Colourless

Packaging

MASTERTOP[®] PRIMER 2 is available in 15kg units.

*Typical properties

Cured at 7 days @20°C	
Pot Life (25°C):	20 mins
Density:	1.09
Bonding strength	Greater than cohesive strength of typical good quality concrete substrate
Application time	approx. 20 mins. at approx. 25°C
Application temperature	10°C to 40°C substrate temp
Recoat after	approx. 6 hours at 30°C approx. 12 hours at 20°C

Guide to application

Cement-bound substrates:

The surface to be coated must be clean and required free of dust, oil and grease; it must be capable of bearing loads. Laitance must be removed by means of captive blasting, grinding or other suitable method.

Mixing:

Pour the B component into the A component then mix until streak free.

On porous surfaces a maximum of 0.5 litres of SOLVENT NO. 2 per 12.4kg unit of Primer may be added to improve penetration.

Application:

Apply by roller brush or airless spray at the required coverage to suit the application for which it is being used.



The Chemical Company

MASTERTOP[®] PRIMER 2

Coverage

From 0.15kg/m² depending on surface texture and porosity.

Storage

Shelf life is minimum 1 year. Store under cover, out of direct sunlight and protect from extremes of temperature. In tropical climates the product must be stored in an air conditioned environment.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult BASF's Technical Services Department.

Safety precautions

Avoid any inhalation of vapours, avoid skin contact! Wear protective gloves and protective goggles! In case of skin contact, rinse immediately with soap and water! In case of eye contact, bathe eyes with water at once, then consult a doctor! Observe the guidelines concerning the handling of epoxy resins and amines issued by the Employer's Liability Insurance Associations.

Note

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

Quality and care

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

06/98 BASF_CC-UAE revised 10/2007

* Properties listed are based on laboratory controlled tests.

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

As all BASF technical datasheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue.

BASF Construction Chemicals UAE LLC

P.O. Box 37127, Dubai, UAE

Tel: +971 4 8090800

Fax: +971 4 8851002

www.basf-cc.ae

