

MASTERTOP[®] TC 400

Single component polyurethane protective traffic coating

Description

MASTERTOP[®] TC 400 is a single component elastomeric pigmented polyurethane coating designed for application in trafficked areas. It provides a pigmented, hard-elastic surface resistant to chemicals and abrasion.

MASTERTOP[®] TC 400 maybe used as an intermediate coating layer in MASTERTOP[®] polyurethane Traffic Deck coating systems.

Primary uses

The high abrasion resistance of MASTERTOP[®] TC 400 combined with its elasticity makes it suitable for use on car park decks.

Advantages

- Excellent impact and abrasion resistance
- Elastomeric
- Weather resistant
- Fire retardant
- Good chemical and oil resistance

Colours

The BASF standard colours for MASTERTOP[®] TC 400 are:

Basalt Grey, Black Grey, May Green, Oxide Red, Brilliant Blue

(Further colours are available on request).

Packaging

MASTERTOP[®] TC 400 is available in 25kg units.

Coverage

From 0.35kg/m² per coat. Please refer to BASF Method Statements for project specific coverages

*Typical properties

Cured at 7 days @20°C	
Density:	1.48 g/cm ³
Viscosity at 23°C, 50 s ⁻¹	800 MPas
Solids content:	83%
Open time at 23°C:	45 min.
Open to foot traffic at 23°C / 50% r.h:	4 hours
Open to vehicular traffic at 23°C / 50% r.h:	16 hours
Tensile strength:	25 N/mm ²
Elongation (ASTM D638):	46%
Tear strength:	45 N/mm ²
Taber Abrasion ASTM D4060 : Part 1	1.02 (g/1000 cycles)

Guide to application

Preparation:

Remove laitance, weak or friable concrete and all contaminants that could affect the bond to the substrate.

Suitable preparation includes light grit blasting, surface grinding etc. Surface defects should be repaired using MASTERTOP[®] Filler 2200 or other suitable repair compounds from the CONCREVIVE or EMACO range.

Priming:

Mix and apply MASTERTOP[®] PRIMER 2 surface conditioner to the prepared dust free surface at approximately 0.15-0.30kg/m². Into the wet primer, scatter a 0.5-1.0kg/m² MASTERTOP[®] SRA No. 3.

Note: If a smooth surface finish is required, omit the aggregate scatter.

Allow to cure.



The Chemical Company

MASTERTOP[®] TC 400

Application

MASTERTOP[®] TC 400 should be stirred before use to ensure uniformity of colour.

Apply by roller, squeegee or airless spray to the primed tack free surface.

Apply at the rate of 0.5–0.9kg / m² (total) in 2-3 coats. MASTERTOP[®] TC 400 can be applied as a single intermediate coat, or as a multi coat sandwich system incorporating aggregates to give a slip resistant finish. When applying as a top coat or part of a multi coat system, do not exceed the maximum overcoating times of the previous coating.

Do not apply when the humidity exceeds 90%. Ensure that the substrate temperature is 3°C higher than the dew point.

If a maintenance coat has to be applied, thoroughly wash the existing MASTERTOP[®] TC 400. Allow to dry, then immediately prior to overcoating, wipe the surface with a cloth dampened with MASTERTOP[®] SOLVENT No. 2.

Chemical resistance

MASTERTOP[®] TC 400 is resistant to acids and alkalis of medium concentrations, mineral oil products and solvents. Contact your local BASF office for specific details.

Shelf life and storage

The shelf life is 6 months in unopened drums in cool and dry conditions.

Once a drum has been opened, its contents should, if possible, be used up completely since surface skinning will form on any remaining quantities.

Safety precautions

Avoid any inhalation of vapour and contact with skin.

Wear protective gloves and protective goggles.

In case of skin contact, rinse immediately with soap and water!

In case of eye contact, bathe eyes with water at once, then consult a doctor.

Do not eat, do not smoke and do not use an open flame when handling the product.

Observe the guidelines issued by the Employer's Liability Insurance Associations.

Note

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.



The Chemical Company

MASTERTOP[®] TC 400

Quality and care

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

06/98 BASF_CC-UAE revised 10/2009

* Properties listed are based on laboratory controlled tests.

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

As all BASF technical datasheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue.

BASF Construction Chemicals UAE LLC

P.O. Box 37127, Dubai, UAE

Tel: +971 4 8090800

Fax: +971 4 8851002

www.basf-cc.ae

