



The Chemical Company

UCRETE[®] TZ/AS

9 - 12 mm Heavy Duty Anti Static Polyurethane Terrazzo Floor Finish

Unique HD Polyurethane Resin Technology with Exceptional Resistance to Aggressive Chemicals and Thermal Shock

Description of Product

UCRETE[®] TZ/AS provides a smooth protective floor finish suitable for applications in predominantly dry environments.

UCRETE[®] TZ/AS is dense and impervious providing the ideal floor finish for applications in pharmaceutical production facilities including process areas, clean room, laboratory, packing hall and warehouse applications and wherever a highly attractive robust long lived floor is required.

UCRETE[®] Industrial Flooring has been widely used throughout industry for more than 30 years, many of the older floors are still in service. A detailed project reference list is available upon request

Temperature Resistance

The UCRETE[®] TZ/AS resins do not start to soften until temperatures above 130°C are exceeded. Specifications are available that are fully serviceable up to 130°C and resistant to occasional spillage up to 150°C.

Correctly installed UCRETE[®] TZ/AS floors can withstand regular and routine spillage of boiling water.

Non Tainting

UCRETE[®] TZ/AS is solvent free and non tainting as tested by the Campden & Choreywood Food Research Association

Chemical Resistance

UCRETE[®] TZ/AS offers exceptional resistance to a wide range of chemical aggressors. For example UCRETE is resistant to spillages of the following commonly encountered classes of chemicals.

Most dilute and concentrated organic acids such as, Acetic acid, Lactic Acid, Oleic Acid and Citric Acid as commonly found in the food industry,

Dilute and concentrated acids: hydrochloric, nitric, phosphoric and sulphuric.

Dilute and concentrated alkalis, including sodium hydroxide to 50% concentration

Animal fats and vegetable oils, sugars flavourings and essences.

Mineral oils, kerosene, gasoline and brake fluids

A wide range of organic solvents including Methanol, Xylene Ethers and Chlorinated solvents



The Chemical Company

UCRETE[®] TZ/AS

Note: some staining or discolouration may occur with some chemicals depending upon the nature of the spillage and the standards of house keeping employed.

Extensive chemical resistance tables are available in the separate data sheet 'A guide to the chemical resistance of UCRETE[®] Flooring'.

For detailed information, please contact your local BASF Construction Chemicals (UK) office for guidance.

Impact Resistance

With high mechanical strengths and a low elastic modulus, UCRETE[®] TZ/AS is very resilient and able to withstand severe impact loads. While no material is indestructible and surface chipping may occur, brittle modes of failure resulting in cracking and disbondment are unknown with UCRETE[®] floors

Cleaning & Hygiene

Regular cleaning and maintenance will enhance the life and appearance of any floor. UCRETE[®] TZ/AS is readily cleaned with industry standard cleaning chemicals and equipment. Please consult your local cleaning chemical or equipment supplier.

Permeability

UCRETE[®] TZ/AS exhibits zero absorption when tested to CP.BM2/67/2.

Substrate Moisture Tolerance

UCRETE[®] Industrial Flooring is extremely tolerant to residual substrate moisture and can be installed directly onto 7 day old concrete, or onto old good quality concrete with high moisture contents without the use of special primers

provided there is a functioning DPM within the structure.

This enables rapid construction programmes to be maintained and facilitates refurbishment work in wet process areas.

Epoxy surface DPMs offer no benefit and should not be used with UCRETE[®] floors.

Colours

UCRETE[®] TZ/AS is available in six standard colours:

Red Yellow Green Orange Grey Cream

Ucrete floor systems have been formulated to provide the very highest chemical and heat resistance. As a direct result some yellowing of the installed floor will occur in areas of direct UV exposure. This is most apparent in lighter colours.

Packaging

UCRETE[®] TZ/AS is supplied as five factory-batched components.

	Mixed Weight
UCRETE PRIMER TC 2 Components	2.41kg
UCRETE MF 4 Components	20.28kg
UCRETE TZ/AS 5 Components	30.63kg
UCRETE TZ Grout 3 Components	6.155kg
UCRETE LOCKCOAT PU	6kg
UCRETE TZ Coving 4 Components	13.10kg

UCRETE® TZ/AS

Coverage

Scratch Coat	UCRETE MF	Approx. 2kg/m ²
Cove Primer	UCRETE PRIMER TC	0.2-0.3kg/m ²
9mm	UCRETE TZ/AS	20-21kg/m ²
12mm	UCRETE TZ/AS	26-27kg/m ²
Pore Sealer	UCRETE TZ Grout	0.2-0.3kg/m ²
1 st Coat Sealer	UCRETE LOCKCOAT PU	0.18-0.21kg/m ²
2 nd Coat Sealer	UCRETE LOCKCOAT PU	0.14-0.16kg/m ²
Coving 6mm	UCRETE TZ Coving (excluding Cove Radius)	12-14kg/m ²

Technical Data

samples cured for 28 days at 20°C

Density (BS 6319:Part 5), Kg/m ³	2090
Compressive strength (BS 6319:Part2), N/mm ²	55
Tensile strength (ISO R527), N/mm ²	6
Flexural strength (ISO 178), N/mm ²	14
Dynamic elastic modulus (ASTMC597-83), N/mm ²	20000
Adhesive strength to concrete (BS6319:Part 4), N/mm ²	concrete failure
Coefficient of thermal expansion (ASTM C531:Part 4 .05), °C ⁻¹	2.4 x 10 ⁻⁵
Thermal conductivity (BS 874), W/m.°C	1.1
Water absorption (CP.BM 2/67/2) ml	0
Surface spread of flame (BS 476:Part7)	Class 2
Sensory evaluation (C&CFRA method TES-S-002)	No taint

Specification

The floor finish shall be UCRETE® TZ/AS from BASF Construction Chemicals (UK), of 19 Broad

Ground Road, Redditch, Worcestershire, B98 8YPB, installed at 9/12* mm in accordance with the manufacturers' instructions

*A 9 mm UCRETE® TZ/AS floor is fully resistant to high temperature spillage and discharge up to 120°C and is fully steam cleanable

*A 12 mm UCRETE® TZ/AS floor is fully resistant to high temperature spillage and discharge up to 130°C and occasional spillage up to 150°C and is fully steam cleanable.

In extreme thermal shock environments a well designed substrate of good quality concrete is essential.

Substrate Quality

Concrete substrates should be visibly dry and have a minimum tensile strength of 1.5 MPa. Refer to the guide 'The Design & Preparation of Substrates for UCRETE® Industrial Flooring'

Curing

Normally UCRETE® TZ/AS floors can be put into service within 24 hours.

Storage

In covered warehouse conditions, above 5°C and below 30°C and out of direct sunlight. Materials must be raised off the floor and kept dry. Parts 1 & 2 must be protected from frost.

Application Conditions

For best results materials, substrate and air temperature should be in the range 5–20°C. Whilst UCRETE® TZ/AS will cure out effectively over a wide range of temperatures the optimum appearance is most readily achieved under good site conditions

UCRETE® TZ/AS

Health and Safety

*For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted.

The following general comments apply to all products.

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs, (which may also be tainted with vapour until the product is fully cured and dried). Treat splashes to eyes and skin immediately.

If accidentally ingested, seek medical attention. Keep away from children and animals. Reseal containers after use.

Solvent Based Products

Use in well ventilated areas; avoid inhaling. Suitable respiratory equipment may be needed, eg when spraying. Can cause skin, eye irritation. Wear protective eye shields and gloves during use. Do not smoke or allow sparks or naked lights when stored or in use.

Powder Products

Should be handled to minimise dust formation; use light mask if excessive dust unavoidable. Cement powders when wet or moistened can cause burns to skin and eyes which should be protected during use.

Resin Products

Can cause irritation, dermatitis or allergic reaction. Use protective equipment particularly for skin and eyes. Use only in well ventilated areas.

Spillage

Chemical products can cause damage; clean spillage immediately

Disclaimer:

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights.

In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied.

We reserve the right to make any changes according to technological progress or further developments.

The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

06/2008 BASF_CC-UAE

* Properties listed are based on laboratory controlled tests.

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

As all BASF technical datasheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue.