

RheoFIT[®] 764

New generation plasticizer for Manufactured Concrete Products, specially engineered for hollow-core slabs, block and paver mixes

Description of Product

RheoFIT[®] 764 is an innovative multi-purpose plasticizer specially developed for semi-dry concrete mixes. The product is suitable for the production of hollow-core slabs, blocks and pavers. At the same time, RheoFIT[®] 764 accelerates the strength development and reduces the cycle time whilst the appearance is maintained or even improved.

Due to its unique principle of action on the cement grain, RheoFIT[®] 764 fully exploits the hydration potential of cement resulting in higher early strengths and shorter curing times.

FIT 4 VALUE:

RheoFIT[®] 764 is a key component to BASF's FIT 4 VALUE concept.

FIT 4 VALUE considers the four elements essential for MCP Manufactures:

1. FIT for Economics
2. FIT for Performance
3. FIT for Aesthetics
4. FIT for Durability

Here, FIT means meeting every requirement for economics, performance, aesthetics and durability.

Fields of Application

RheoFIT[®] 764 is suitable for Manufacturing Concrete Products, especially:

- Pavers
- Blocks
- Hollow-core slabs

Features and Benefits

RheoFIT[®] 764 offers the following benefits for the MCP industry to:

- Optimised mix design
- Enhanced productivity due to shorter cycle time
- Higher early strength
- Optimised curing cycles due to shorter curing times

Packaging

RheoFIT[®] 764 is available in 210 litre drums or bulk.

Application Procedure

RheoFIT[®] 764 is a liquid ready-to-use admixture to be added to the concrete during the mixing process. The best results are obtained when the admixture is added after all the other components are already in the mixer and after the addition of at least 80% of the total water. The water content is adjusted to obtain the desired consistence or workability.

RheoFIT[®] 764

*Technical Data/Typical Properties

Appearance	dark brown free-flowing liquid
Specific gravity @ 25°C	1.205
pH-value	7 - 10

Standards

EN 934-2 Table 3.1 and 3.2

Dosage rate

The normally recommended dosage rate is 0.4 to 1.2 litres per 100kg of cement.

Other dosages may be used in special cases according to specific job site conditions. In this case please consult our Technical Services Department.

Compatibility

RheoFIT[®] 764 is compatible and recommended for use with:

- RheoFIT[®] 742, colour enhancer
- RheoFIT[®] 744, water repellent, to reduce water absorption (e.g. EN 1338, class 2 B)
- Rheofinish 299C, cleaning and protection agent

RheoFIT[®] 764 is not compatible with RheoFIT[®] 763, 700, 701, 703 or GLENIUM superplasticizers.

Storage

RheoFIT[®] 764 must be stored in a place where the temperature does not drop below 5°C.

If stored in unopened containers according to manufacturer's instructions, the shelf life is 2 years.

Handling and transportation

No special requirements must be observed while the product is used. Protection gloves and glasses are recommended. Do not eat, drink or smoke during the application. RheoFIT[®] 764 is non-flammable, non-toxic or irritant and is not subject to special transport requirements.

Note

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

Quality and care

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

10/2006 BASF_CC-UAE revised 04/2008

* Properties listed are based on laboratory controlled tests.

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

As all BASF technical datasheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue.