

GLENIUM® 112

New polycarboxylic ether superplasticizer for the production of high quality ready-mix concrete with low water cement ratio and exceptional workability

Description

GLENIUM® 112 is an innovative latest generation superplasticizer based on polycarboxylic ether (PCE) polymers, and is specially engineered for ready-mix concrete.

GLENIUM® 112 is differentiated from conventional superplasticisers, such as those based on sulphonated melamine and naphthalene formaldehyde condensates in that it is based on a unique carboxylic ether polymer with long lateral chains. This greatly improves cement dispersion. At the start of the mixing process the same electrostatic dispersion occurs but the presence of the lateral chains, linked to the polymer backbone, generate a steric hindrance which stabilises the cement particles capacity to separate and disperse.

This mechanism provides flowable concrete with greatly reduced water demand.

Fields of application

GLENIUM® 112 is used for the production of high quality ready-mix concrete.

Features and Benefits

GLENIUM® 112 offers the following benefits for:

The ready-mix producer:

- Capability of delivering high performance concrete at any time to the job site in place
- Production of a concrete with low water cement ratios without loss of workability
- Single product for many application needs

The contractor / applicator:

- Easier placing and faster strength development
- Improved concrete surfaces
- Guarantee to place the same concrete as specified and ordered from ready-mix plant

The engineer:

- Insurance that concrete meets original specification
- High quality durable concrete

Packaging

GLENIUM® 112 is supplied in 210 litre drums, 1,000 litre containers or in bulk.

*Typical properties

Appearance	Medium to dark brown coloured liquid
Specific gravity @ 25°C	1.055
pH value	5.0
Chloride content	"chloride-free" to EN 934-2

Standards

ASTM C-494 Type F&G
ASTM C-1017 Type I & II
EN 934-2, Tables 11.1 and 11.2

Application procedure

Dosage

The normally recommended dosage rate of GLENIUM® 112 is 0.8 to 2.0 litre per 100kg of total cementitious material.

Other dosages may be recommended in special cases according to the specific site conditions. In this case please consult our Technical Services Department for advice.

GLENIUM® 112

Mixing

GLENIUM® 112 is a ready-to-use admixture to be added to the concrete as a separate component. Optimal result is obtained if GLENIUM® 112 is poured into the concrete mix right after the addition of the first 80% of the mixing water, i.e. when all solids are wetted. Avoid adding the admixture to the dry aggregates.

Compatibility

GLENIUM® 112 is not compatible with RHEOBUILD® superplasticizers.

In order to optimize special requirements the use of the following complementary additives is suggested:

- Air entraining agent MICRO-AIR® to improve frost/thaw resistance

GLENIUM® 112 is suitable for mixes containing:

- Microsilica
- Fly Ash (PFA)
- ground granulated blast furnace slag cement (GGBS)

Storage

GLENIUM® 112 should be stored out of direct sunlight and protected from extremes of temperature. The shelf life is 9 months when stored as above.

Handling and transportation

No special requirements must be observed during use. Protection gloves and glasses are however recommended. GLENIUM® 112 is non-flammable, non-toxic or irritant and is not subject to special transport requirements.

Safety precautions

GLENIUM SKY 112 contains no hazardous substances requiring labelling. For further information refer to the Material Safety Data Sheet.

Note

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

Quality and care

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

03/2008 BASF_CC-UAE revised 02/2012

* Properties listed are based on laboratory controlled tests.

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

As all BASF technical datasheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue.