

POZZOLITH[®] LD60

Low dosage, high performance plasticising and strength increasing admixture for concrete with set retardation properties

Description

POZZOLITH[®] LD60 is a high performance concrete plasticiser and water reducing agent. Unlike conventional lignosulphonate plasticisers it possesses the ability to increase early and ultimate strengths even at constant water cement ratios.

POZZOLITH[®] LD60 is designed to optimise hydration of the cement paste, subject to the mix design. When compared to a control concrete 28 days strengths are achievable in 7 days and similarly 7 days strengths are achievable within 3 days.

POZZOLITH[®] LD60 is a versatile product which can be utilised throughout a varying range of temperatures. It can be used as a standard plasticiser in the low dosage range through to a powerful retarder at the high dosage range.

Primary uses

- To increase workability.
- To increase compressive strength.
- Hot weather concreting.
- To effect cement economies.

Typical applications

POZZOLITH[®] LD60 is used wherever optimum workability and maximum strengths are required such as:

- In areas of congested reinforcement where high workability is of benefit.
- Hot weather concreting where controlled delays to initial set are beneficial.
- Readymix concrete where workability retention coupled with retardation of initial set are beneficial.

- Concrete mixes containing mineral admixtures such as PFA, where maximum workability and maximum strength gain is beneficial.

Advantages

- Highly effective over wide range of cement contents.
- Higher early and ultimate strengths.
- Low dosage.
- Improves workability whilst at the same time increasing compressive strength.
- Permits water reduction, in the region of 10% to 15%.
- Increases impermeability and durability.
- Reduces placing problems in hot weather concreting by improving workability and workability retention.
- Improves surface finish, pumpability and trowellability.
- Enables significant economies in mix design to be achieved thereby saving cement.

Packaging

POZZOLITH[®] LD60 is available in bulk or in 210 litre drums.

Compatibility

POZZOLITH[®] LD60 can be used with all types of Portland cement including sulphate resisting and modified cement (Type II). For use with special cements contact BASF's Technical Services Department. POZZOLITH[®] LD60 should not be premixed with other admixtures.

If other admixtures are to be used in concrete containing POZZOLITH[®] LD60, they must be dispensed separately. Consult BASF's Technical Services Department for advice.



The Chemical Company

POZZOLITH[®] LD60

If other admixtures are to be used in concrete containing POZZOLITH[®] LD60, they must be dispensed separately. Consult BASF's Technical Services Department for advice.

Standards

EN 934-2 Tables 2 and 10

ASTM C494 : Types A, B and D

BS 5075 : Part 1 (superseded by EN 934-2)

*Typical properties

Colour:	Dark brown liquid
Specific gravity:	1.220 at 25°C
Chloride content:	"chloride free" to EN 934-2
Freezing point:	0°C

Action

POZZOLITH[®] LD60 acts on the cement particles by combining the effects of powerful plasticising and deflocculating agents. It considerably improves the workability of concrete mixes without the addition of extra water. The improved dispersion of the cement particles ensures the process of hydration proceeds under the optimum conditions.

Directions for use

POZZOLITH[®] LD60 should be added to the concrete mix during the mixing cycle at the same time as the water or the aggregates. Never add POZZOLITH[®] LD60 to the dry cement. No extension to normal mixing times is necessary.

Dosage

Depending on performance requirements POZZOLITH[®] LD60 has a normal dosage range from 300ml to 1100ml per 100kg of cement or cementitious material. Higher dosages may be required when certain combinations of materials and conditions are present.

In all cases we recommend trial mixes are carried out to determine the correct levels of admixture required to achieve the desired concrete properties.

Setting time

POZZOLITH[®] LD60 provides controlled retardation to initial set. Setting times of concrete mixes are related to cement type and ambient temperature.

Effects of over dosage

A severe over dosage of POZZOLITH[®] LD60 will result in the following:

- Retardation of initial and final set.
- Slight increase in air entrainment.
- Increase in workability.

Providing it is properly cured, the ultimate strength of the concrete will not normally be adversely affected and will generally be higher than for normal concrete. The retarding effect of over dosage will be exaggerated with SRC cement.

Dispensing

POZZOLITH[®] LD60 should be dispensed through a proprietary dispenser, such as is available from BASF UAE. Details upon request.

Storage

Store under cover, out of direct sunlight and protect from extremes of temperature.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advices consult BASF's Technical Services Department.



The Chemical Company

POZZOLITH[®] LD60

Safety precautions

POZZOLITH[®] LD60 is not a fire or health hazard. Spillages should be washed down immediately with cold water. For further information refer to the material safety data sheet.

Note

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

Quality and care

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

04/2002 BASF_CC-UAE revised 04/2008

* Properties listed are based on laboratory controlled tests.

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

As all BASF technical datasheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue.

BASF Construction Chemicals UAE LLC

P.O. Box 37127, Dubai, UAE

Tel: +971 4 8090800

www.basf-cc.ae

Fax: +971 4 8851002

e-mail: marketingcc.mideast@basf.com



Certificate No.
963680



Certificate No.
945787



Certificate No.
772556