

RHEOBUILD[®] 1110

A high range water reducing superplasticising admixture for the production of rheoplastic concrete

Description

The basic components of RHEOBUILD[®] 1110 are synthetic polymers which allow mixing water to be reduced considerably and concrete strength to be enhanced significantly, particularly at early ages. RHEOBUILD[®] 1110 is a chloride free product.

Primary uses

- Production of rheoplastic concrete.
- Precast concrete.
- Low water/cement ratio concrete.
- In complicated formwork or with congested reinforcement.

Advantages

RHEOBUILD[®] 1110 allows the production of very workable low water / cementitious concrete. Concrete with RHEOBUILD[®] 1110 shows strengths higher than concrete without admixture having the same workability. The increase in strength, specially evident at early ages remains at later ages, both in air cured and steam cured processes. Initial and final sets do not change significantly with respect to concrete without admixture.

Due to the reduction in the water / cement ratio, all other properties of hardened concrete improve significantly, namely; lowered permeability, shrinkage and creep, increased workability and modulus of elasticity.

For more detailed information on the influence of superplasticisers on hardened concrete properties, consult your local BASF representative.

Compatibility

RHEOBUILD[®] 1110 can be used with all normal types of Portland Cement and cementitious materials such as GGBS, Fly Ash or micro silica.

The use of RHEOBUILD[®] 1110 and MICRO-AIR 100 air entraining agent is recommended whenever concrete is required to withstand freeze / thaw cycling.

Packaging

RHEOBUILD[®] 1110 is available in bulk or 210 litre drums.

*Typical properties

Colour:	Brown free flowing liquid.
Specific gravity:	1.225 at 25°C.
Air entrainment:	Maximum 1%.
Chloride content:	Chloride free to EN 934
Nitrate content:	Nil.
Freezing point:	0°C. Can be reconstituted if stirred after thawing.

Standards

ASTM C-494 Types A and F
EN 934

Dosage

RHEOBUILD[®] 1110 is normally dispensed at a rate of 0.7-1.4 litres per 100kg of cementitious material. Subject to successful trials, other dosages may be used up to a rate of 2.5 litres per 100kg of cementitious material.

Directions for use

RHEOBUILD[®] 1110 should be added to the mix with the gauging water.

RHEOBUILD[®] 1110

No extension to the mixing time is necessary. Never add RHEOBUILD[®] 1110 to dry cement.

Alternatively, when using RHEOBUILD[®] 1110 to produce flowing concrete at site using ready mix trucks, it can be added to the concrete via the feed hopper at the rear of the truck. Mix before discharge for 3 minutes at 10rpm to produce a fully homogenous mix.

When using RHEOBUILD[®] 1110 to obtain very high early strengths, advantage must be taken of its water reducing properties.

Effects of over dosage

A severe over-dosage of RHEOBUILD[®] 1110 will result in the following:

- Retardation of initial and final set.
- Slight increase in air entrainment.
- Increase in workability.

Dispensing

RHEOBUILD[®] 1110 is introduced into the mixer together with mixing water. The plasticising effect or water reduction is higher if the admixture is added to the concrete after 50-70% of the mixing water has been added. The addition of RHEOBUILD[®] 1110 to dry aggregate or cement is not recommended.

Storage

Store under cover, out of direct sunlight and protect from extremes of temperature. Shelf life is at least 2 years when stored as above. Failure to comply with the recommended storage conditions may result in premature deterioration

of the product or packaging. For specific storage advice consult BASF's Technical Services Department.

Safety precautions

RHEOBUILD[®] 1110 contains no hazardous substances requiring labelling. For further information refer to the material safety data sheet.

Note

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

Quality and care

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

03/2008 BASF_CC-UAE

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

As all BASF technical datasheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue.

BASF Construction Chemicals UAE LLC

P.O. Box 37127, Dubai, UAE

Tel: +971 4 8090800

www.basf-cc.ae

Fax: +971 4 8851002

e-mail: marketingcc.mideast@basf.com



Certificate No.
963680



Certificate No.
945787



Certificate No.
772556