

MASTERTILE[®] 40

Cementitious tile adhesives for ceramic tiles

Description

MASTERTILE[®] 40 is a grey cementitious powder formulated as a high performance fixing adhesive for a wide range of applications.

Typical applications

Ceramic wall and floor tiles in internal applications. MASTERTILE[®] 40 may be employed with confidence in institutional or high traffic conditions. MASTERTILE[®] 40 is suitable for use in kitchens, showers and wet process areas. For external applications use MASTERTILE[®] 30.

Advantages

- Water resistant.
- Precision made.
- Easy to use.
- Economical.
- For walls and floors
- High adhesive bond strength.

Packaging

MASTERTILE[®] 40 is available in 25kg bags.

Composition

MASTERTILE[®] 40 is a blend of Portland cement, graded sand and organic polymer.

*Typical properties

Colour	Grey
Plastic density	1.80
Flash point	None
Service temperature	-30°C - +100°C
Application temperature	+5°C to +35°C

Yield

25kg bag mixed with 4.5-5 litres of water yields approximately 16.2 litres of mixed adhesive.

Coverage

Solid bed fixing:	3mm - 6mm depth 5.4kg - 10.8 kg/m ²
Notched trowel:	smooth surface 2kg/m ²

Application procedure

Surface preparation:

All surfaces must be clean, dimensionally stable, sound and free from all traces of oil, grease, mould release agent and curing compound. It should be ensured that tiles are dry, and free of contaminants that could impair adhesion.

Concrete, screeds, renders, and blockwork should be cured sufficiently that all shrinkage movement has occurred.

Mixing instructions:

Add MASTERTILE[®] 40 to cool, clean water at the following rates:

By weight 4.5-5:1, Volume 2.5:1. Mix to a uniform lump free consistency and allow to stand for 5 minutes before use. Full bag volumes should ideally be mixed in a forced action mixer. Part bags should be mixed using a slow speed drill and mixing paddle.

Application instructions:

Apply MASTERTILE[®] 40 to a uniform thickness of 3 to 6mm or sufficient to cover the studs or keys on the tile back; on a working area of not more than 1 m². Solid bed fixing is recommended for all horizontal applications and for ceramic tiles. If preferred, MASTERTILE[®] 40 can additionally be



The Chemical Company

MASTERTILE[®] 40

buttered on the backs of the tiles to ensure full adhesive contact. For all other vertical applications the adhesive bed should be combed horizontally with a notched trowel to remove excess.

Tiles should be dry and fixed by pressing into place with slight twisting motion, ensuring the tile back achieves full contact with the adhesive.

Note: Do not apply over an area greater than that which can be covered within the open time of the product.

Ceramic tiles should never be butt jointed. Leave a minimum of 2mm around tiles.

Adjustments to tiles should only be made during the adhesives open time.

Remove excess adhesive from the face of the tile with a damp sponge or cloth before it sets. Similarly, joints must be raked out in readiness for grouting.

Leave for a minimum of 24 hours before grouting. Select the appropriate grout for joint size and in service use from the MASTERTILE[®] range.

Watchpoints

Movement joints should be provided in accordance with normal practice. Refer to published local standards or BS 5385.

MASTERTILE[®] 40 should not be used, unless modified with MASTERTILE[®] 200, on painted or metal surfaces, existing glazed tiled surfaces, or to bond non porous or high density ceramics such as glass mosaics.

Tiles should not be soaked in water prior to application.

Gypsum plaster boards and surfaces, must be subjected to pre-treatment. Please consult BASF Technical Services for further advice.

Do not apply MASTERTILE[®] 40 greater than 8mm thickness on horizontal surfaces and 6mm on vertical surfaces.

Codes of practice

Tiling and grouting should be carried out in accordance with relevant British Standard Codes of Practice.

Safety precautions

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek immediate medical attention.

Storage

Store out of direct sunlight, clear of the ground on pallets protected from rainfall. Avoid excessive compaction.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult BASF's Technical Services Department.



The Chemical Company

MASTERTILE[®] 40

Note

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

Quality and care

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

08/95 BASF_CC-UAE revised 07/2009

* Properties listed are based on laboratory controlled tests.

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

As all BASF technical datasheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue.

BASF Construction Chemicals UAE LLC

P.O. Box 37127, Dubai, UAE

Tel: +971 4 8090800

Fax: +971 4 8851002

www.basf-cc.ae

