

# MASTERPREN<sup>®</sup> RE

## Synthetic membrane of plasticised PVC

### Description

MASTERPREN RE is a synthetic membrane made by the co-extrusion process. Made of plastisol layers, with different chemical & physical properties and has a layer of glass fibre inserted, for dimensional stability.

### Typical applications

MASTERPREN RE can be applied in the following circumstances:

- Upstands and exposed areas in conjunction with membranes needing protection i.e. Masterpren RC
- Covered and inverted Roof Structures
- Landscaped areas and Roof Gardens
- Underground Structures

### Advantages

- It has superior mechanical characteristics and is resistant to weathering and ultra violet rays
- High mechanical properties and resistance to puncturing
- Rot-proof
- Vapour permeable
- Resistance to root penetration
- If double welded it allows pressure testing of joints
- Can be bonded on verticals with the Masterpren PVC Adhesive
- Good resistance to hydrocarbons and bacterial attack
- Long life expectancy

### Packaging and roll sizes

MASTERPREN RE is supplied in various thicknesses with 1.60 and 2.10 meter width and in lengths of 20 meters.

Thickness (mm)	1.2	1.5	1.8	2.0	2.4
Width (m)	1.60	1.60	1.60	1.60	1.60
Width (m)	2.10	2.10	2.10	2.10	2.10
Length (m)	20	20	20	20	20
Colour	Light grey				

### Application procedure

Usually applied by Specialist Applicator. Please contact BASF Construction Chemicals for specific application assistance.

### Watertight Systems & Engineered Solutions

BASF Construction Chemicals provide systems and engineered solutions, to suit the structure, at the design and construction stages, to ensure watertightness. Various products and elements which form an integral part of a system are manufactured and approved by BASF. The following ranges of products are available;

- Masterpren range – Preformed membranes
- Masterflex range - Active and passive joint treatment
- Masterseal range - Liquid applied membranes and protective coatings
- Masterflow range - High performance grouts
- Emaco and Concrevice ranges - Repair materials

### Storage

Store out of direct sunlight, clear of the ground and on pallets.

### Note

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF Construction Chemicals representative.

BASF reserves the right to have the true cause of any liability determined by accepted test methods.

# MASTERPREN<sup>®</sup> RE

## \*Physical / Chemical Properties

Thickness UNI EN 1849 - 2	1.2mm	1.5mm	1.8mm	2.0mm	2.4mm
Specific weight (kg/m <sup>2</sup> ) UNI EN 1849 - 2	1.50	1.80	2.15	2.40	2.90
Tensile strength UNI EN 12311 - 2	≥ 9.0 N/mm <sup>2</sup>	≥ 9.0 N/mm <sup>2</sup>	≥ 9.0 N/mm <sup>2</sup>	≥ 9.0 N/mm <sup>2</sup>	≥ 9.0 N/mm <sup>2</sup>
Elongation to break UNI EN 12311 - 2	≥ 200%	≥ 200%	≥ 200%	≥ 200%	≥ 200%
Tear resistance UNI EN 12310 - 2	≥ 110N	≥ 135N	≥ 160N	≥ 170N	≥ 200N
Puncture resistance DIN 16726 - 5.12	≥ 450mm	≥ 800mm	≥ 900mm	≥ 1000mm	≥ 1500mm
Cold bending UNI EN 495 - 5	≤ - 25°C	≤ - 25°C	≤ - 25°C	≤ - 25°C	≤ - 25°C
Hydrostatic pressure resistance (6 hours at 5 bar) UNI EN 1928 meth. B	waterproof	waterproof	waterproof	waterproof	waterproof
Dimensional stability after 6 hours at 80°C – UNI EN 1107 - 2	≤ ± 0.1%	≤ ± 0.1%	≤ ± 0.1%	≤ ± 0.1%	≤ ± 0.1%
Resistance to artificial weathering UNI EN 1297	no cracking	no cracking	no cracking	no cracking	no cracking
Root resistance DIN 4062	No penetration	No penetration	No penetration	No penetration	No penetration
Resistance to hail on rigid substrate NI EN 13583	≥ 25 m/s	≥ 25 m/s	≥ 25 m/s	≥ 25 m/s	≥ 25 m/s
Thermal ageing in air after 168 d at 70°C Cold bending UNI EN 1296	≤ - 25°C	≤ - 25°C	≤ - 25°C	≤ - 25°C	≤ - 25°C
Peel resistance of joints UNI EN 12316 - 2	≥ 150 N/50 mm	≥ 150 N/50 mm	≥ 150 N/50 mm	≥ 150 N/50 mm	≥ 150 N/50 mm
Shear resistance of joints UNI EN 12317 - 2	Breaking out of joint	Breaking out of joint	Breaking out of joint	Breaking out of joint	Breaking out of joint
Resistance to impact UNI EN 12691	20 mm	20 mm	10 mm	10 mm	10 mm
Resistance to static punching UNI EN 12316	≥ 20 kg	≥ 20 kg	≥ 20 kg	≥ 20 kg	≥ 20 kg

### Quality and care

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational Health & Safety standards ISO 9001, ISO 14001 and OHSAS 18001.

10/2007 BASF\_CC-UAE revised 03/2010

\* Properties listed are based on laboratory controlled tests which are carried out immediately after production.

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

**As all BASF technical datasheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue.**

### BASF Construction Chemicals UAE LLC

P.O. Box 37127, Dubai, UAE

Tel: +971 4 8090800

Fax: +971 4 8851002

www.basf-cc.ae

