

THOROSEAL®

Cement based coating for waterproofing concrete and masonry.

Description

THOROSEAL® is a blend of Portland cements, well graded sands and additives supplied in powder form.

Uses

- For interior and exterior waterproofing of concrete and masonry, above and below ground level, for example, tanking of basements, water reservoirs, tunnels, swimming pools, lift pits, concrete pipes, food troughs, fish tanks, etc.
- As a replacement for external rendering systems.
- As a waterproof coating on walls and floors of showers, bathrooms and toilets before the fixing of tiles.

Benefits

- **Durable**
Resists positive and negative water pressure.
Above and below ground level.
Water vapour permeable.
High bond strength, becomes integral part of the substrate.
Blocks the pores of concrete through penetration.
- **Cost effective**
Good application rate.
- **Easy to apply**
Can be brushed or sprayed.
To be applied on a damp substrate.
Equipment to be cleaned simply with water.
- **Environmentally friendly**
Cement based.
No solvents.

Packaging

25 kg pail or sack and 10 kg pail.

Colours

Standard: white, grey and pearl grey.

*Typical properties

Typical values. All tests were carried out under temperature controlled conditions of 21°C.

| | | |
|---|-------|-------------------------|
| Maximum particle size | | 0.8 mm |
| Water vapour permeability $\mu\text{H}_2\text{O}$ | | 86 - 120 |
| Resistance to neg. pressure | | 4 bar |
| <u>Mechanical strengths</u> | | <u>N/mm²</u> |
| Compressive | 28 d | 55.0 |
| Tensile | 28 d | 3.7 |
| Flexural | 28 d. | 7.6 |
| Adhesive | 28 d | 2.5 |

Application

Substrate preparation

The surface to be coated must be clean and sound.

Remove all traces of formwork, release agents, previous coatings, laitance and any contaminants that may affect the bond adversely.

Suitable cleaning methods include high-pressure water treatment and grit blasting. NOT recommended are aggressive percussive methods such as scabbling. After the above treatment, surfaces must be thoroughly washed with clean potable water to remove all dust and loose particles.

Cracks and bolt holes must be cut out and filled solid with WATERPLUG, THORO STRUCTURITE or THORO STRUCTURITE 300.

THOROSEAL®

Mixing

Wet density 2.08 kg/dm³

Pot life 45 minutes

Final setting time 300 minutes

Mixing liquid

1 part THORO ACRYL 60 /

3 parts clean water

± 5.2 litres (4.8 – 5.6) liquid / 25 kg powder

Blend 25 kg of powder into approximately 5.2 litres of liquid (1 part THORO ACRYL 60 / 3 parts water) or an equal amount of water only. The quantity may vary slightly depending upon the ambient conditions. In all instances, it is important that the material is mixed to the correct consistency.

In applications where the THOROSEAL® is expected to be in contact with hydrocarbons (such as diesel oil, petrol, etc.), potable water only should be used as mixing liquid.

In this case up to a maximum of 6.1 litres per 25 kg of powder may be used.

Power mixing

Blend the powder into the mixing liquid using a THORO EZ mixer attachment in a slow-speed drill (400 – 600 rpm). Mix until a thick, batter-like consistency is obtained. Leave the THOROSEAL® to stand for 5 - 10 minutes to allow full saturation to take place. Re-mix, adding a small quantity of liquid if required, to restore the consistency.

Do not exceed the maximum liquid demand.

Hand mixing

Add the mixing liquid to the powder whilst stirring with a trowel or paddle to the consistency described above. Leave the THOROSEAL® to stand for 10-20 minutes to allow full saturation to take place. Re-mix, adding a small quantity of liquid if required, to restore the consistency.

Application

Do not apply THOROSEAL® to frozen substrates or if the ambient temperature is below 5°C or expected to fall below 5°C within 24 hours.

Avoid application in direct sunlight.

Always apply the mix to a pre-dampened surface. High suction substrates require more dampening than dense substrates. However, make sure there is no free-standing water. Apply by specially designed THORO brush or broom. Mixed material must be used within 45 minutes, or less under hot weather conditions.

First coat

Brush or broom the mix firmly onto the pre-dampened, prepared surface. After completing 2 or 3 m², strike off with the brush or broom in one direction for aesthetic purposes. Care must be taken not to spread the material too thinly.

When the material begins to drag or “ball”, do not add more liquid, but dampen the surface again.

Second coat

Allow at least overnight to cure before applying subsequent coats. Dampen the first coat and remove excess moisture. Brush or broom the mix onto the surface (as above) finishing in the opposite direction to the previous coat.

THOROSEAL® can be spray applied but should afterwards be brushed well into the substrate to ensure proper adhesion.

To improve the aesthetic appearance an additional layer can be applied by spray, eventually sponge floated to give a uniform surface.

THOROSEAL[®]

Curing

Under hot or excessive drying conditions fog-spray after the initial set has taken place for as long as practicable in cold, humid or unventilated areas it may be necessary to leave the application for a longer curing period or to introduce forced air movement. NEVER use dehumidifiers during curing periods.

Coverage

A two layer application will require a minimum of 2.5 kg powder per m². Note that the quantities required may increase by up to 50% on rough substrates.

Storage

THOROSEAL[®] should be stored under cover, clear of the ground and stacked not more than 6 sacks or 2 pails high. Protect the materials from all sources of moisture and frost. Rotate stock in order not to exceed the shelf life of 12 months for pails and 6 months for sacks.

Clean up and spillages

Not hardened material may simply be removed with water.

Additional information

THOROSEAL[®] fills pores and voids, forms a closely meshed material and contains water-repellent additives. Condensation may occur after waterproofing basement areas. It could last for a considerable period in poorly ventilated areas and is most likely to form in areas which were previously damp. The formation of condensation can be alleviated by increasing the ventilation and/or plastering the walls with a lightweight, cement-based plaster.

THOROSEAL[®] is not suitable for retaining water with a low calcium hardness and/or a pH of less than 7.2 (THOROSEAL[®] FX100 may be used for this application). Nor is suitable for application to horizontal surfaces that are subject to freeze/thaw cycles or vehicular traffic.

If THOROSEAL[®] is used to waterproof a potable water reservoir, a swimming pool or a fish tank, it should be washed down after the curing completed with a saline solution (salt brine), 12.5% of salts in water, and thoroughly rinsed with clean water. This process should be repeated until the required pH conditions are obtained.

Sulphate contaminated substrates exposed to negative water pressure should be treated with THOROSEAL[®] SULFABAR.

Health and safety

THOROSEAL[®] is based on cement and can be irritating to the skin and eyes. Gloves and eye protection should be worn. The use of dust masks is recommended. Accidental splashes of the material to the skin or eyes should be immediately washed off with clean water. In the event of prolonged irritation seek medical advice. In the case of ingestion give water or milk to drink and treat symptomatically. Medical advice should be sought.

A Material Safety Data Sheet is available on request.

10/2006 BASF_CC-UAE revised 05/2012

* Properties listed are based on laboratory controlled tests.

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

As all BASF technical datasheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue.